

**ICEA STANDARD FOR  
TELECOMMUNICATIONS CABLE  
FILLED, POLYOLEFIN INSULATED, COPPER CONDUCTOR  
TECHNICAL REQUIREMENTS**

Published By

INSULATED CABLE ENGINEERS ASSOCIATION, INC.  
Post Office Box 1568  
Carrollton, GA 30112, U.S.A.

Fifth Edition

© 2010 by ICEA

Approved March 3, 2010 by  
Insulated Cable Engineers Association, Inc.

Approved by ANSI ASC C-8  
American National Standards Institute

Copyrighted by the ICEA  
Contents may not be reproduced  
in any form without permission of the  
INSULATED CABLE ENGINEERS ASSOCIATION, INC.

Copies of this publication may be obtained from:

IHS  
15 Inverness Way East  
Englewood, CO 80112-5776 USA  
Telephone: (800) 854-7179  
[www.ihs.com](http://www.ihs.com)

## **NOTICE AND DISCLAIMER**

The information in this publication was considered technically sound by the consensus of persons engaged in the development and approval of the document at the time it was developed. Consensus does not necessarily mean that there is unanimous agreement among every person participating in the development of this document.

The Insulated Cable Engineers Association, Inc. (ICEA) standards and guideline publications, of which the document contained herein is one, are developed through a voluntary consensus standards development process. This process brings together persons who have an interest in the topic covered by this publication. While ICEA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy or completeness of any information or the soundness of any judgements contained in its standards and guideline publications.

ICEA disclaims liability for personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, application, or reliance on this document. ICEA disclaims and makes no guaranty or warranty, expressed or implied, as to the accuracy or completeness of any information published herein, and disclaims and makes no warranty that the information in this document will fulfill any of your particular purposes or needs. ICEA does not undertake to guarantee the performance of any individual manufacturer or seller's products or services by virtue of this standard or guide.

In publishing and making this document available, ICEA is not undertaking to render professional or other services for or on behalf of any person or entity, nor is ICEA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgement or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. Information and other standards on the topic covered by this publication may be available from other sources, which the user may wish to consult for additional views or information not covered by this publication.

ICEA has no power, nor does it undertake to police or enforce compliance with the contents of this document. ICEA does not certify, test, or inspect products, designs, or installations for safety or health purposes. Any certifications or other statement of compliance with any health or safety-related information in this document shall not be attributable to ICEA and is solely the responsibility of the certifier or maker of the statement.

(page intentionally left blank)

## FOREWORD

ICEA Standards are published in the public interest and are intended to promote product uniformity and quality throughout the industry. Existence of an ICEA publication does not in any respect preclude the manufacture or use of products not conforming to the Standard.

The user of this Standard is cautioned to observe any applicable health or safety regulations and rules relative to the manufacture and use of cable made in conformity with this Standard. This Standard hereafter assumes that manufacture, testing, installation and maintenance of cables defined by this Standard will be performed only by properly trained personnel using suitable equipment and employing appropriate safety precautions.

Questions of interpretation of ICEA Standards can only be accepted in writing and the reply shall be provided in writing. Suggestions for improvements in this Standard are welcome. Questions and suggestions shall be sent to:

Secretary  
Insulated Cable Engineers Association  
P.O. Box 1568  
Carrollton, GA 30112  
United States of America

This Standard was developed by the ICEA Communications Division, WG-608. It was approved by ICEA on March 3, 2010.

The members of the ICEA Communications Division, Working Group 608 who participated in this project were:

P. Fraley  
G. Dorna

D. K. Baker  
T. Zou  
D. Taylor

J. Baer  
T. McLaughlin

The following participated in an advisory capacity to WG-608:

Joe Mafnas

RUS

**TABLE OF CONTENTS**

CONTENTS:	SECTION	PAGE
1.	<b><u>GENERAL</u></b>	
1.1	PURPOSE.....	1
1.2	SCOPE.....	1
1.3	OPTIONS AND INFORMATION .....	1
1.4	UNITS AND TOLERANCES.....	2
1.5	REFERENCES.....	2
1.6	QUALITY ASSURANCE.....	2
1.7	SAFETY CONSIDERATIONS .....	3
2.	<b><u>CONDUCTORS</u></b>	
2.1	REQUIREMENTS .....	3
2.2	FACTORY JOINTS .....	4
3.	<b><u>CONDUCTOR INSULATION</u></b>	
3.1	INSULATION MATERIALS .....	4
3.1.1	Propylene/Ethylene Copolymer.....	4
3.1.2	High-Density Polyethylene .....	4
3.1.3	Medium-Density Polyethylene.....	4
3.2	INSULATION TYPE .....	4
3.2.1	Solid .....	4
3.2.2	Foam.....	4
3.2.3	Foam-Skin.....	4
3.3	INSULATION DIMENSIONS, COLORS, AND SPLICES .....	4
3.4	INSULATION PHYSICAL REQUIREMENTS .....	5
3.4.1	Insulation Adhesion.....	5
3.4.2	Elongation .....	5
3.4.3	Compression.....	5
3.4.4	Cold Bend .....	6
3.4.5	Shrinkback .....	6
3.4.6	Thermal Oxidative Stability .....	6
3.5	TWIST LENGTH AND COLOR CODING .....	6
4.	<b><u>CORE CONSTRUCTION</u></b>	
4.1	CORE LAYUP .....	7
4.2	BINDERS .....	9
4.3	SPARE PAIRS .....	9
4.4	CORE WRAP .....	10
4.5	FILLING COMPOUND .....	10
4.5.1	Type Filling Compound .....	11
4.5.2	Adequacy of Fill .....	11

**TABLE OF CONTENTS**

CONTENTS:	SECTION	PAGE
	4.6 FLOODING COMPOUND .....	11
	4.7 WATER SWELLABLE MATERIALS.....	11
5.	<b><u>INTERNAL SCREENS</u></b>	
	5.1 DESCRIPTION.....	11
	5.2 SCREEN MATERIAL .....	12
	5.2.1 Film Delamination .....	12
	5.3 SERVICE PAIRS.....	12
6.	<b><u>SHIELDS</u></b>	
	6.1 SHIELDING SYSTEMS.....	12
	6.2 SHIELD MATERIALS.....	13
	6.2.1 8-mil Bare Aluminum Tape.....	13
	6.2.2 8-mil Coated Aluminum Tape.....	13
	6.2.3 5-mil Copper Tape .....	13
	6.2.4 5-mil Copper Clad Alloy Steel Tape .....	13
	6.2.5 5-mil Copper Clad Stainless Steel Tape .....	14
	6.2.6 6- and 7-mil C194 Copper Alloy Tape .....	14
	6.2.7 5-mil C230 Copper Alloy Tape .....	14
	6.2.8 6-mil Bare Steel Tape .....	14
	6.2.9 6-mil Coated Steel Tape .....	15
	6.3 SHIELD APPLICATION.....	15
	6.3.1 Shield Corrugation .....	15
	6.3.2 Shield Overlap .....	15
	6.3.3 Shield Splices .....	16
	6.4 CORROSION RESISTANCE TEST .....	16
	6.5 GOPHER RESISTANCE TEST .....	16
7.	<b><u>POLYETHYLENE INNER AND OUTER JACKET</u></b>	
	7.1 INNER JACKET .....	17
	7.1.1 Material and Test Requirements .....	17
	7.1.2 Inner Jacket Thickness Requirement.....	17
	7.2 OUTER JACKET .....	17
	7.2.1 Raw Material .....	17
	7.2.2 Outer Jacket Thickness Requirement.....	18
	7.2.3 Completed Cable Material Requirements .....	18
	7.2.4 Shrinkback .....	20
	7.2.5 Sheath Adherence-Unbonded.....	20
	7.2.6 Sheath Adherence-Bonded.....	20

**TABLE OF CONTENTS**

CONTENTS:	SECTION	PAGE
8.	<b><u>ELECTRICAL REQUIREMENTS</u></b>	
8.1	DC RESISTANCE .....	21
8.2	DC RESISTANCE UNBALANCE .....	21
8.3	MUTUAL CAPACITANCE .....	21
	8.3.1 Final Product 100 % Testing .....	21
8.4	CAPACITANCE DIFFERENCE .....	22
8.5	PAIR-TO-PAIR CAPACITANCE UNBALANCE .....	22
8.6	PAIR-TO-GROUND CAPACITANCE UNBALANCE .....	22
8.7	ATTENUATION .....	22
8.8	UNIT CROSSTALK .....	22
	8.8.1 Crosstalk Qualification Test .....	23
8.9	BETWEEN-COMPARTMENT CROSSTALK FOR SCREENED CABLES .....	24
	8.9.1. Requirements for all Applications .....	24
	8.9.2 Requirements for T-1C and Similar Applications .....	24
	8.9.3 Qualification Test Procedure .....	24
8.10	INSULATION RESISTANCE .....	25
8.11	CONDUCTOR-TO-CONDUCTOR DC PROOF TEST .....	25
8.12	CORE-TO-SHIELD DC PROOF TEST .....	25
8.13	CORE-TO-SCREEN DC PROOF TEST .....	26
8.14	SHIELD RESISTANCE .....	26
8.15	CONTINUITY OF METALLIC CABLE ELEMENTS .....	26
9.	<b><u>MECHANICAL REQUIREMENTS</u></b>	
9.1	COMPOUND FLOW .....	26
9.2	WATER PENETRATION .....	26
9.3	CABLE BEND TEST .....	27
	9.3.1 Cold Bend Test .....	27
	9.3.2 Hot Bend Test .....	27
9.4	CABLE IMPACT .....	27
9.5	CABLE TORSION TEST .....	27
10.	<b><u>GENERAL REQUIREMENTS</u></b>	
10.1	IDENTIFICATION AND MARKING .....	28
	10.1.1 Identification .....	28
	10.1.2 Length Marking .....	29
	10.1.3 Defective Pair Marking .....	28
	10.1.4 Communication Cable Identifier .....	29
10.2	END SEALING .....	29



**TABLE OF CONTENTS**

CONTENTS:	SECTION	PAGE
	10.3 INFORMATION ACCOMPANYING THE REEL .....	29
	10.4 OPTIONAL REQUIREMENTS .....	29
	10.4.1 Physical Reel Protection .....	29
	10.4.2 Pulling Eyes .....	29

**TABLES**

Table 1:	Specifications Referenced in This Standard .....	31
Table 2-1	Conductor Diameter.....	3
Table 2-2	Conductor Elongation .....	4
Table 3-1	Insulation Colors .....	5
Table 3-2	Conductor Adhesion .....	5
Table 3-3	Insulation Compression .....	6
Table 3-4	Color Code and Pair Designation .....	7
Table 4-1	Unit Binder Color Code .....	8
Table 4-2	Super-Unit Binder Color Code .....	8
Table 4-3	Color Code for Spare or Service Pairs.....	10
Table 6-1	Tape Thickness .....	14
Table 6-2	Composition Limits.....	15
Table 6-3	Gopher Damage Descriptions.....	16
Table 7-1	Jacket Thickness .....	18
Table 7-2	Jacket Material Requirements .....	19
Table 8-1	Conductor Resistance.....	21
Table 8-2	Resistance Unbalance .....	21
Table 8-3	Mutual Capacitance .....	21
Table 8-4	Capacitance Unbalance to Ground.....	22
Table 8-5	Attenuation.....	22
Table 8-6	PSELFEXT .....	23
Table 8-7	PSNEXT .....	23
Table 8-8	Conductor-to-Conductor DC Proof Test.....	25
Table 8-9	Core-to-Shield Dc Proof Test.....	26
Table 10-1	Pulling Eye Load Factors .....	30

**FIGURES**

Figure 1:	Forming of Steel Tape Overlap.....	34
Figure 2:	Sheath Adherence Sample Preparation.....	35

**TABLE OF CONTENTS**

CONTENTS:           SECTION.....PAGE

**APPENDICES**

Appendix A: Standard Internally Screened (IS) Cable Pair Counts..... 36  
Appendix B: Metallic Tape Splice Breaking Strength, Percent Retention..... 37  
Appendix C Corrosion Resistance..... 38

**ANNEXES**

Informative Annex A: Product Guide for ANSI/ICEA S-84-608-20XX..... A-1  
Informative Annex B: ICEA Telecommunication Cable Standards ..... B-1

**ACRONYMS, ABBREVIATIONS AND SYMBOLS**

ANSI	American National Standards Institute
ASTM	American Society for Testing and Materials
AWG	American Wire Gauge
°C	Degrees of Temperature, Celsius scale, Centigrade
dB	decibel
dc	Direct Current
EIA	Electronic Industries Alliance
ELFEXT	Equal Level Far-End Crosstalk
°F	Degrees of Temperature, Fahrenheit scale
ft	foot or feet
g	gram
ICEA	Insulated Cable Engineers Association
in	inch
ISO	International Organization for Standardization
kHz	kilohertz
kV	kilovolt
lb	pounds
lbf	pounds of force
MHz	Megahertz
m	meter
mm	millimeter
Mpa	megapascal
N	Newton
nF	nanofarad
NEXT	Near-End Crosstalk
NESC	National Electrical Safety Code
ns	nanoseconds
pF	picofarad
psi	pounds per square inch
PSELFEXT	power sum equal level far end crosstalk
PSNEXT	power sum near end crosstalk
rms	root mean square
$\alpha$	Attenuation

(page intentionally left blank)

## **ICEA STANDARD FOR FILLED, POLYOLEFIN INSULATED, COPPER CONDUCTOR TELECOMMUNICATIONS CABLE TECHNICAL REQUIREMENTS**

### SECTION 1 GENERAL

- 1.1 **PURPOSE:** The purpose of this Standard is to establish generic technical requirements that may be referenced by individual telecommunications cable specifications covering products intended for normal outside plant use. The parameters covered provide material, construction, and performance requirements that are applicable to filled, polyolefin insulated and jacketed cables of all pair counts, including a variety of shield and jacket combinations and optional compartmental screening.

Because this Standard does not cover all details of individual cable design, it cannot be used as a single document for procurement of product. It is intended to be used in conjunction with an individual product specification that provides complete design details for the specific cable type and designates the applicable performance requirements. Such individual cable specifications may be prepared either by the user or the manufacturer. The specification designated for procurement is at the option of the user.

- 1.2 **SCOPE:** This Standard covers mechanical and electrical requirements for filled, polyolefin insulated, copper conductor telecommunications cable. It provides alternative choices for type of insulation, type of filling compound, core lay-ups, color code, sheath design (shielding materials, single or double jackets, and jacket thicknesses), and screened or non-screened core.